

**IN THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application.

**Listing of Claims:**

Claims 1-11 (Canceled)

Claim 12 (Original) A method of producing a microporous polyolefin membrane, comprising the steps of extruding the solution, composed of 10 to 50 weight % of (A) a polyolefin having a weight-average molecular weight of  $5 \times 10^5$  or more or (B) a composition containing this polyolefin and 50 to 90 weight % of a solvent, into a gel-like formed article and removing the solvent therefrom, wherein a treatment step with a hot solvent is incorporated.

Claim 13 (Original) The method of producing a microporous polyolefin membrane according to Claim 12, wherein said treatment step with a hot solvent is effected at from the crystal dispersion temperature to melting point plus  $10^\circ\text{C}$  of said (A) polyolefin or (B) polyolefin composition.

Claim 14 (Currently Amended) The method of producing a microporous polyolefin membrane according to Claim 12 ~~or 13~~, wherein said treatment step with a hot solvent is effected prior to said step of removing the solvent.

Claim 15 (Currently Amended) The method of producing a microporous polyolefin membrane according to Claim 12 ~~or 13~~, wherein said treatment step with a hot solvent is effected subsequent to said step of removing the solvent.

Claim 16 (Currently Amended) The method of producing a microporous polyolefin membrane according to Claim 12 ~~to 15~~, wherein said polyolefin (A) has a weight-average molecular weight of  $1 \times 10^6$  to  $15 \times 10^6$ .

Claim 17 (Currently Amended) The method of producing a microporous polyolefin membrane according to Claim 12 ~~to 15~~, wherein said polyolefin composition (B) is composed of an ultra-high-molecular-weight polyolefin having a weight-average molecular weight of  $1 \times 10^6$  to  $15 \times 10^6$  and a polyolefin having a weight-average molecular weight of  $1 \times 10^5$  or more but less than  $1 \times 10^6$ .

Claim 18 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of~~ Claim 12 ~~to 15~~, wherein said polyolefin composition (B) contains an ultra-high-molecular-weight polyolefin having a weight-average molecular weight of  $7 \times 10^5$  or more at 1 weight % or more.

Claim 19 (Currently Amended) The method of producing a microporous polyolefin

membrane according to ~~one of Claims~~ Claim 12 to 18, wherein said polyolefin (A) or polyolefin composition (B) has a weight-average molecular weight/number-average molecular weight ratio ( $M_w/M_n$ ) of 300 or less.

Claim 20 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 18, wherein said polyolefin (A) or polyolefin composition (B) has a weight-average molecular weight/number-average molecular weight ratio ( $M_w/M_n$ ) of 5 to 50.

Claim 21 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 19, wherein said polyolefin (A) or polyolefin for said composition (B) is polypropylene or polyethylene.

Claim 22 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 21, wherein the average pore size (a) in the area from the surface to a depth of  $d/16$  (d: thickness of said membrane) is 0.05 to  $50\mu\text{m}$ , preferably 1 to  $30\mu\text{m}$ , and the average pore size (b) in the other area is 0.01 to  $30\mu\text{m}$ , preferably 0.03 to  $2\mu\text{m}$ , where the relationship  $(b) < (a)$  should hold.

Claim 23 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 15 or Claim 17, wherein said polyolefin

composition (B) is composed of a polyolefin having a weight-average molecular weight of  $5 \times 10^5$  or more and polyolefin having a weight-average molecular weight of 1,000 to 4,000 and melting point of 80 to 130°C.

Claim 24 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 15 or Claim 17, wherein said polyolefin composition (B) is composed of (B-1) an ultra-high-molecular-weight polyolefin having a weight-average molecular weight of  $5 \times 10^5$  or more and (B-2) a polyolefin having a weight average molecular weight of less than  $5 \times 10^5$ , the (B-2)/(B-1) weight ratio being 0.2 to 20.

25. (Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 15 or Claims 17 to 22, wherein said polyolefin composition (B) is composed of a polyolefin having a weight-average molecular weight of  $5 \times 10^5$  or more and polypropylene having a weight-average molecular weight of  $3 \times 10^5$  or more.

26. (Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 15 or Claims 17 to 22, wherein said polyolefin composition (B) is composed of a polyolefin having a weight-average molecular weight of  $5 \times 10^5$  or more and ethylene-based copolymer having a melting point of 95 to 125°C and produced in the presence of a single-site catalyst.

Claim 27 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 15 or Claims 17 to 22, wherein said polyolefin composition (B) is composed of 1 to 69 weight % of an ultra-high-molecular-weight polyolefin having a weight-average molecular weight of  $7 \times 10^5$  or more, 98 to 1 weight % of a high-density polyethylene, and 1 to 30 weight % of a low-density polyethylene.

Claim 28 (Currently Amended) The method of producing a microporous polyolefin membrane according to ~~one of Claims~~ Claim 12 to 27, wherein stretching said gel-like article is an essential step.

Claim 29 (Original) The method of producing a microporous polyolefin membrane according to Claim 28, wherein said stretching step is effected at an areal ratio of 15 to 400.

Claim 30 (Original) A battery separator which uses the microporous polyolefin membrane according to Claim 1.

Claim 31 (Original) A battery which uses the microporous polyolefin membrane according to Claim 1 for its separator.

Claim 32 (Canceled)